

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C09J 167/04	A1	(11) International Publication Number: WO 94/10257 (43) International Publication Date: 11 May 1994 (11.05.94)
(21) International Application Number: PCT/US93/08913 (22) International Filing Date: 20 September 1993 (20.09.93) (30) Priority data: 968,564 29 October 1992 (29.10.92) US 000,153 4 January 1993 (04.01.93) US (71) Applicant: NATIONAL STARCH AND CHEMICAL INVESTMENT HOLDING CORPORATION [US/US]; 501 Silverside Road, Wilmington, DE 19809 (US). (72) Inventors: IOVINE, Carmine, P. ; 263 White Oak Ridge, Bridgewater, NJ 08807 (US). KAUFFMAN, Thomas, F.; 1809 Meadow Lane Drive, Easton, PA 18042 (US). SCHOENBERG, Jules, E. ; 39 Tunison Lane, Bridgewater, NJ 08807 (US). PULETTI, Paul, P. ; RD#3, P.O. Box 344, Hill Hollow Road, Pittstown, NJ 08867 (US).		(74) Agent: DEC, Ellen, T.; National Starch and Chemical Company, P.O. Box 6500, Bridgewater, NJ 08807 (US). (81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: POLYLACTIDE CONTAINING HOT MELT ADHESIVE (57) Abstract Hot melt adhesive compositions are prepared from 20 to 98 % by weight of a polylactide homo- or copolymer containing at least 20 molar percent of the lactide component; 2 to 80 % by weight of a polar tackifier having a Ring and Ball softening point (as described by ASTM E-26) greater than about 60 °C; 0 to 50 % by weight of a plasticizer; 0 to 30 % by weight of a wax diluent; 0-3 % by weight of a stabilizer; and 0-20 % of a polymer. By utilizing a naturally occurring, thermoplastic, biodegradable copolymer as the base polymer, these adhesives advance the state of the art of hot melt adhesives by alleviating the dependence on petroleum based materials and by allowing for the development of hot melt adhesives which either degrade naturally after coming in contact with the soil or which can be composted.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TC	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

POLYLACTIDE CONTAINING HOT MELT ADHESIVE**BACKGROUND OF THE INVENTION**

5 Hot melt adhesives are used commercially for a wide variety of applications. The major advantage of hot melt adhesive systems is the lack of a carrier fluid which eliminates the need for drying the adhesive film once it is applied to the substrate. This elimination of the
10 drying step overcomes hazards associated with solvent usage and also allows for faster production line speeds and lower transportation costs. Depending on the desired use, the degree of tack of the hot melt adhesives may be varied over a wide range to produce adhesives varying
15 from pressure sensitive to non-pressure sensitive in character. Non-pressure sensitive are used, for example, in bookbinding, bag ending, case and carton sealing. Pressure sensitive hot melts are used in many applications, and particularly in disposables such as
20 diapers, sanitary products and the like, where room temperature tack and long open time are required. Hot melt adhesives have historically been based on petroleum derived polymers such as polyethylene, ethylene-vinyl acetate, styrenic block copolymers, and
25 polypropylene to name a few. These compositions are further tackified, plasticized, and reinforced with a variety of resins, oils and waxes which are derived from both petroleum and naturally occurring feedstocks such as wood, gum and tall oil rosin and terpenes. These classic
30 compositions suffer from the cyclical price cycles common to all oil derived materials, and also are generally very resistant to degradation once the articles employing them are disposed of.

35 The present invention stems from the growing movement away from petroleum derived raw materials to

those derived from renewable, natural resources and as part of an effort to utilize raw materials which have demonstrated some level of degradation. The present invention utilizes a class of naturally occurring or
5 synthetically produced thermoplastic, biodegradable copolymers derived from a non-petroleum feedstock as the base polymer. Such compositions advance the state of the art of hot melt adhesives by alleviating the dependence on petroleum based materials and by allowing for the
10 development of hot melt adhesives which either degrade naturally after coming in contact with the soil or which can be composted.

SUMMARY OF THE INVENTION

It has been discovered that hot melt adhesive
15 compositions suitable for a variety of applications are obtained by use of polylactide (i.e., the bimolecular cyclic ester of lactic acid) or copolymers with other lactones such as glycolide and caprolactone, tackifiers, and
20 optionally, waxes and/or plasticizers. The adhesives may be formulated using conventional additives and may vary from pressure sensitive to non-pressure sensitive in character depending upon the desired application.

In its broadest aspect, the present invention is
25 directed to hot melt adhesive compositions comprising 20 to 98% by weight of a polylactide homo- or copolymer where the copolymer contains at least 20 molar percent of the lactide component (l or d or d,l or meso or mixtures thereof) 2 to 80% by weight of a polar tackifier having
30 a Ring and Ball softening point (as described by ASTM E-26) greater than about 60°C; 0 to 50% by weight of a plasticizer; 0 to 30% by weight of a wax diluent and 0-3% by weight of a stabilizer.

It will be recognized that the general formulations
35 described above can be adapted to include a wide variety of hot melt adhesive compositions, the more precise formulations of which will vary depending upon the

specific end use, the knowledge of which is readily available to those skilled in the particular art.

Thus, in general, pressure sensitive adhesives can be prepared using 20 to 70% by weight of the polylactide homo- or copolymer, 10 to 60% of a tackifying resin, 10 to 50% plasticizer and 0 to 3% of a stabilizer. Preferred pressure sensitive adhesives are prepared using 30 to 60% of the polylactide homo- or copolymer; 20 to 50% of a tackifying resin, preferably a terpene phenolic resin; and 20 to 30% of a plasticizer, preferably Pycal 94, a phenyl ether of poly(ethylene glycol) from ICI; or Hercules. Lower levels of plasticizer may also be employed to produce adhesives useful for various end uses such as in construction adhesives for disposable products where some initial degree of tack is needed but no residual pressure sensitive properties are required.


In general, non-pressure sensitive adhesives can be prepared using 20-98% by weight of the polylactide homo- or copolymer, 2-80% tackifying resin, 0-30% of a wax-like diluent, 0-30% plasticizer and 0 to 3% of a stabilizer. Preferred non-pressure sensitive adhesives are prepared using 30-80% of the polylactide homo- or copolymer; 10-40% tackifying resin, preferably terpene-phenolic resins or rosin derivatives; 0-25% of a plasticizer, preferably the phenyl ether of poly(ethylene glycol) or the methyl ester of hydrogenated wood rosin; and 0-20% of a wax-like diluent, preferably hydrogenated castor oil (also known as castor wax) or 12-hydroxystearamide.

Additionally, polymers other than the polylactide may be incorporated into the hot melt adhesives at levels less than about 20% by weight. Representative formulations and applications are discussed hereinbelow and illustrated by the examples, however, these should not be construed as limiting the invention.

DETAILED DESCRIPTION OF THE INVENTION

The major component of the adhesive of the invention, present in an amount of 20 to 98% by weight of

the adhesive, comprises a homo- or copolymer of polylactide containing at least 20 molar percent of the lactide comonomer. The general structure of the polylactide is shown below:



Suitable polymers for use herein have a number average molecular weight (M_n) within the range of 10,000 to 200,000.

15 While poly(d,l-lactide) and the meso- are essentially amorphous, poly(l-lactide) and poly(d-lactide) is crystalline in nature and has a crystalline melting point of 186°C depending on its molecular weight and stereopurity. The polymers may be prepared by ring-
20 opening polymerization of the bimolecular cyclic ester of lactic acid with acid or base catalysts such as PbO, SnCl₂, SnCl₄, ZnCl₂, SbF₅, Sb₂O₃, or triethylamine using solution, precipitation or melt processes. Alternatively, they may be obtained commercially from
25 Henley Chemicals, Inc. under the Resomer® tradename; from Poly Sciences Inc. or from Ecological Chemical Products Company (EcoChem).

In addition to homopolymers of poly(l-lactide), poly(d-lactide), poly(d,l-lactide), and poly(meso-lactide)
30 suitable polymers for use herein may also be prepared by copolymerization with other lactones such as glycolide or caprolactone. Thus, poly(d,l-lactide-co-glycolide) polymers containing equimolar amounts of the lactide and glycolide components are available from Henley Chemicals
35 as Resomer RG502, 503, 504, 505 and 506 and are suitable for use herein. In addition, poly(d,l-lactide-co-glycolide) polymers known as Resomer RG752, 755 and 756 containing 75% of the lactide component as well as the

SUBSTITUTE SHEET

Resomer 858 polymer which contains 85% lactide are also suitable.

The tackifying resins useful in the adhesive compositions are generally polar in nature and have a Ring and Ball softening point greater than 60°C and include rosin and rosin derivatives, terpene phenolics, pure phenolic resins, and the like. More particularly, the useful tackifying resins include any compatible resins or mixtures thereof such as (1) natural and modified rosins such, for example, as gum rosin, wood rosin, tall oil rosin, distilled rosin, hydrogenated rosin, dimerized rosin, and polymerized rosin; (2) glycerol and pentaerythritol esters of natural and modified rosins, such, for example as the glycerol ester of pale, wood rosin, the glycerol ester of hydrogenated rosin, the glycerol ester of polymerized rosin, the pentaerythritol ester of hydrogenated rosin, and the phenolic-modified pentaerythritol ester of rosin; (3) phenolic modified terpene resins and hydrogenated derivatives thereof such, for example, as the resin product resulting from the condensation, in an acidic medium, of a bicyclic terpene and a phenol; (4) thermoplastic alkyl phenolic resins such as those described in U.S. Patent Nos. 4,073,776 and 4,023,826. Mixtures of two or more of the above described tackifying resins, as well as blends of the above resins with small amounts of (e.g., less than about 10% of the adhesive) less compatible resins may be utilized for some formulations. While the tackifier may comprise up to about 80% of the adhesive, it is generally used in amounts of 10 to 60% by weight.

Depending on the end-use application, and particularly for uses requiring pressure sensitive properties, various compatible plasticizing or extending oils may also be present in the composition. Preferred compatible plasticizers include phthalate plasticizers such as dioctyl phthalate; liquid polyesters such as Dynacol 720 from Huls; benzoate plasticizers such as 1,4-

SUBSTITUTE SHEET

cyclohexane dimethanol dibenzoate (e.g., Benzoflex 352 available commercially from Velsicol); phosphate plasticizer such as t-butylphenyl diphenyl phosphate (e.g., Santicizer 154 available commercially from Monsanto); poly(ethylene glycols) and derivatives thereof such as the phenyl ether of poly(ethylene glycol) (e.g., Pycal 94 available commercially from ICI) as well as liquid rosin derivatives having Ring and Ball melting points below about 60°C such as the methyl ester of hydrogenated rosin (e.g., Hercolyn D from Hercules); as well as vegetable and animal oils such as glyceryl esters of fatty acids and polymerization products thereof.

Other applications conventionally employing adhesives based on these polylactide polymers may require the use of wax diluents in order to reduce the melt viscosity or cohesive characteristics of the hot melt adhesive compositions without appreciably decreasing their adhesive bonding characteristics. These waxes are often used in adhesives which do not exhibit pressure sensitive properties.

Suitable waxes include 12-hydroxystearamide wax, hydrogenated castor oil, oxidized synthetic waxes, poly(ethylene oxide) having a weight average molecular weight above about 1000 and functionalized synthetic waxes such as carbonyl containing Escomer H101 from Exxon.

It should be recognized that some adhesive formulations described herein may contain both wax and plasticizer components so that the presence of one or the other is not mutually exclusive.

Among the applicable stabilizers or antioxidants which may be included herein are high molecular weight hindered phenols and multifunctional phenols such as sulfur and phosphorous-containing phenols. Representative hindered phenols include: 1,3,5-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene; pentaerythritol tetrakis-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate; n-octadecyl 3,5-di-

SUBSTITUTE SHEET

tert-butyl-4-hydroxyphenyl) propionate; 4,4'-methylene-bis (2,6-di-tert-butylphenol); 4,4'-thiobis (6-tert-butyl-o-cresol); 2,6-di-tert-butylphenol; 6-(4-hydroxyphenoxy)-2,4-bis(n-octylthio)-1,3,5-triazine; di-n-octadecyl-3,5-di-tert-butyl-4-hydroxy-benzylphosphonate; 2-(n-octyl-thio)-ethyl 3,5-di-tert-butyl-4-hydroxybenzoate; and sorbitol hexa[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate]. If used, the stabilizer is present in levels of about 0.1 to 3% by weight.

Optional additives may be incorporated into the hot melt compositions in order to modify certain properties thereof. Among these additives may be included colorants such as titanium dioxide; and fillers such as talc and clay, etc. There may also be present in the adhesive small amounts (e.g., less than about 20% by weight, and preferably 5 to 20% by weight) of certain thermoplastic polymers such as ethylene vinyl acetate, ethylene acrylic acid, ethylene methyl acrylate and ethylene n-butyl acrylate copolymers containing about 12 to 50% vinyl acetate as well as caprolactone polymers. These polymers are employed in order to impart flexibility, toughness and strength. Alternatively and in particular, it may be desirable to incorporate into the hot melt adhesive up to 20% by weight of certain hydrophilic polymers such as poly(vinyl alcohol), hydroxyethyl cellulose, starch, modified starch, poly(vinyl methyl ether), poly(ethylene oxide), or poly(hydroxy butyrate/hydroxy valerate) which will function to increase the water sensitivity of the adhesives which may be desired for some applications.

These hot melt adhesive compositions may be formulated using techniques known in the art. An exemplary procedure involves placing approximately 40% of the total tackifying resin concentration with all the polymer, wax, plasticizers and stabilizers in a jacketed mixing kettle, preferably in a jacketed heavy duty mixer, which is equipped with rotors and thereupon raising the temperature to a range of from up to about 190°C. After the resin has melted, the temperature is lowered to 150°

SUBSTITUTE SHEET

to 165°C. Mixing and heating are continued until a smooth, homogeneous mass is obtained whereupon the remainder of the tackifying resin is thoroughly and uniformly admixed therewith.

5 The adhesives disclosed herein may be employed in a wide variety of uses as are known in the art. The adhesives described herein may be effectively utilized in a variety of packaging and carton sealing applications. The non-pressure sensitive adhesives may also be used to
10 bind a plurality of sheets in a wide range of bookbinding operations. They may also be used for laminating tissue and/or screen-reinforced tissue layers such as are used in individual or roll use applications as in wipers, paper towels, toilet tissue and other consumer or
15 industrial end uses. When formulated with plasticizers, the resultant adhesives may be used in the assembly or construction of various disposable applications including, but not limited to, sanitary napkins, disposable diapers, hospital gowns, bed pads and the
20 like. In particular, adhesives are useful for the assembly of disposable articles using multi-line construction techniques wherein at least one flexible film substrate is bonded to at least one tissue, non-woven, polyolefin or other flexible polymeric film
25 substrate. In addition, the adhesives may be useful in the bonding of elastic to polyethylene, polypropylene or non-woven substrate so as, for example, to impart elongation resistant gathers thereto. The adhesive may also be utilized in less demanding disposable
30 construction applications such as for end or perimeter sealing.

In the following illustrative examples all parts are given by weight and all temperatures in degrees Celsius unless otherwise noted.

35

EXAMPLE I

In preparing the following samples, a heavy duty mixer which had been heated to 190°C and which was equipped with a stirring paddle was charged with 40% of

SUBSTITUTE SHEET

the tackifying resin, and/or diluent. After melting of the resins, stirring was then initiated whereupon the polylactide was added slowly at 190°C over a one-half hour period after which the temperature was lowered to 170°C. Heating and stirring were continued until a homogeneous mass was obtained whereupon the remainder of the tackifying resin and/or diluent was admixed therewith. The samples were tested using the following procedures:

Viscosity measurements were determined after 30 minutes using a Brookfield viscometer (Spindle 27) at 350°F.

The adhesive was also subjected to Peel/Shear testing such as is conventionally required in the packaging industry. Peel Temperature Test: A bead of test adhesive approximately 1/8 inch in diameter is applied at 325°F to 350°F with a glass rod onto 60 pound/ream kraft paper. A second sheet of the same paper is superimposed on the first sheet within 2 seconds and pressed thereto to form a kraft-to-kraft bond. The bonded sheets are then cut perpendicular to the adhesive line into 1 inch wide strips. Duplicate bonded specimens are placed in an oven with one free end of the specimen attached to a fixed support and a 100 gram load suspended from the other sheet at the same end of the bond. The oven temperature is then increased in 10°F increments at 15 minute intervals. The temperature at which bond delamination occurred is specified as the peel temperature.

Shear Temperature Test: Samples are prepared as in peel temperature test but separate sheets of Kraft at opposite ends of the bonded specimen are suspended and weighted to stress the bond in a shear mode. The temperature of the oven is increased as in peel test until failure occurs.

Adhesion Test: A molten bead of hot melt at 325°F to 350°F was drawn across the middle (widthwise) of a 1" x 3" strip of Kraft paper. A second strip of Kraft paper

SUBSTITUTE SHEET

was then immediately superimposed upon the first and a 50 gram weight placed on top of the construction. The Kraft to Kraft bonds were then aged 24 hours at either room temperature (RT or 70°F) or at 40°F. After aging, the samples were stressed by hand at the temperature of storage in a 90° peel mode. The presence or absence of fiber tear was then noted.

The compositions and the results of the testing are shown in Table I.

10

TABLE I

	1	2		4	5	6	7	Poly(1-lactide)	
15	Poly(1-lactide)	21.5	18.0	15.0	15.0	17.0	15.0	15.0	----
	Hercolyn D	7.5	9.0	9.0	6.0	10.0	9.0	9.0	----
	PEG-200	1.0	3.0	----	----	----	----	----	----
	Pycal 94	----	----	3.0	6.0	3.0	3.0	3.0	----
	Nirez 300	----	----	3.0	3.0	----	----	----	----
20	Super Fluidity Hylon VII	----	----	----	----	----	3.0	----	----
	40% VA, EVA	----	----	----	----	----	3.0	----	----
	Compat-ibility	Yes	Yes	Yes	Yes	Yes	Yes	Yes	----
25	DSC Tg Tm	47°C 169°	32°C 160°	N/T 161° C	N/T 159° C	N/T 162° C	- 4°C 161° C	31°C 162° C	75°C 186°C ----
30	Viscosity (cps) @	N/T	235	80	N/T	100	N/T	N/T	----
	350°F	N/T	120	>200	N/T	>200	120°	120°	----
	Peel (°F)	N/T	>200	F.T.	N/T	F.T.	>200	>200	----
35	Shear (°F)	N/T	F.T.	F.T.	N/T	F.T.	°	°	----
	Adhesion (Kraft)						F.T.	F.T.	
	RT (40°)						F.T.	F.T.	

Hercolyn D - methyl ester of hydrogenated rosin from Hercules
 PEG-200 - polyethylene glycol from Union Carbide
 Pycal 94 - phenyl ether of polyethylene glycol from ICI
 Nirez 300 - terpene- phenolic resin from Arizona Chemical
 N/T - not tested
 Super Fluidity Hylon VII - modified starch propionate

The test results presented above show the adhesives to be particularly suitable for packaging applications

SUBSTITUTE SHEET

such as case and carton sealing due to its low viscosity, good fiber tear and acceptable peel and shear values.

Similar performance results would be expected from the use of comparable amounts of poly(d,l-lactide) or copolymers thereof, however, due to the more amorphous nature of the poly(d,l-lactide) the later polymers would be particularly suitable for hot melt pressure sensitive applications.

Another series of hot melt adhesives were formulated and tested as described above. In this series, the adhesives were also tested for thermal stability by storing at 350°F for 72 hours and then noting the appearance of the adhesive.

The compositions and test results are shown in Table II.

TABLE II

	8	9	10
Poly(l-lactide)	25.0	25.0	25.0
Hercolyn D	---	15.0	15.0
Pycal 94	15.0	---	---
Nirez 300	10.0	---	10.0
Foral NC	---	10.0	---
Irganox 1010	0.1	0.1	0.1
Viscosity @ 350°F	335 cps	470 cps	4125 cps
Peel	100	>80°F	140
Shear	>200	150	>200
Adhesion RT	F.T.	F.T.	F.T.
40°F	F.T.	F.T.	F.T.
Thermal Stability (72 hours/350°F)	None	Yes	None
Skin	None	None	None
Gel	Brown	Black	Light
Color	None	Yes	Brown
Separation	None	None	None
Char	15 cps	---	None
Final Viscosity @ 350°F			175 cps

Foral NC is a calcium salt of rosin from Hercules
Irganox 1010 is a hindered phenol antioxidant from Ciba
Geigy

5 The results presented in Table II indicate that
samples 8 and 10 have acceptable thermal stability for
most applications. It is also to be noted that the
thermal stability may be even further improved by pre-
drying of the polylactide polymer since the polymer picks
up moisture when stored as a raw material.

10 The results also show that sample 10 would be
particularly suitable for industrial bag applications
where high heat resistance and relatively higher
viscosity are required. Sample 8 shows particular use
for case and carton sealing. Sample 9, while not having
15 as high a degree of heat resistance, would nonetheless be
suitable for less stringent heat resistant applications
such as bottle labelling.

SUBSTITUTE SHEET

CLAIMS

1. A hot melt adhesive composition comprising 20 to 98% by weight of a polylactide mono- or copolymer containing at least 20 molar percent of the lactide component; 2 to 80% by weight of a polar tackifier having a Ring and Ball softening point (as described by ASTM E-26) greater than about 60°C; 0 to 50% by weight of a plasticizer; 0 to 30% by weight of a wax diluent and 0-3% by weight of a stabilizer.
2. The adhesive of Claim 1 wherein the polylactide is a homopolymer of l- or d,l-lactide.
3. The adhesive of Claim 1 wherein the polylactide is a co-polymer of (l-lactide) or (d,l-lactide) with glycolide or caprolactone.
4. The adhesive of Claim 1 wherein the polylactide has a number average molecular weight within the range of 10,000 to 200,000.
5. The adhesive of Claim 1 wherein the tackifying resin is selected from the group consisting of (1) natural and modified rosins; (2) glycerol and pentaerythritol esters of natural and modified rosins; (3) phenolic modified terpene resins and hydrogenated derivatives thereof; (4) thermoplastic alkyl phenolic resins; and mixtures thereof.
6. The adhesive of Claim 1 wherein the plasticizer is selected from the group consisting of phthalate plasticizers; liquid polyesters; benzoate plasticizers; phosphate plasticizers; poly(ethylene glycols) and derivatives thereof; and liquid rosin derivatives having Ring and Ball melting points below about 60°.

7. The adhesive of Claim 1 wherein the wax is selected from the group consisting of hydroxy stearamide wax, hydrogenated castor oil, oxidized synthetic waxes, poly(ethylene oxide) having a weight average including
5 weight above about 1000 and functionalized synthetic waxes.

8. The adhesive of Claim 1 wherein there is also present up to 20% by weight of a thermoplastic polymer selected from the group consisting of polycaprolactone
10 ethylene vinyl acetate, ethylene acrylic acid, ethylene methyl acrylate and ethylene n-butyl acrylate copolymers containing 12 to 50% comonomer.

9. The adhesive of Claim 1 wherein there is also present up to 20% by weight of a polymer selected from
15 the group consisting of polyvinyl alcohol, hydroxyethyl cellulose, polyvinyl methyl ether, poly(ethylene oxide), or poly(hydroxy butyrate hydroxy valerate).

10. The adhesive of Claim 1 wherein there is also present up to 20% by weight starch or modified starch.

20 11. A hot melt pressure sensitive adhesive composition comprising 20 to 70% by weight of a polylactide homo- or copolymer containing at least 20 molar percent of the lactide component, 10 to 60% of a tackifying resin, 0 to 3% of a stabilizer and 10 to 50% plasticizer.

25 12. The adhesive of Claim 11 comprising 30 to 60% of the polylactide copolymer; 20 to 50% of the tackifying resin, 20 to 30% of the plasticizer and 0 to 3% stabilizer.

13. The adhesive of Claim 11 wherein the polylactide polymer is poly(d,l-lactide) or a copolymer thereof.

14. The adhesive of Claim 11 wherein the tackifying resin is a terpene phenolic and the plasticizer is a phenyl ether of poly(ethylene glycol).

5 15. The adhesive of Claim 11 wherein there is also present up to 20% by weight of a thermoplastic polymer selected from the group consisting of polycaprolactone ethylene vinyl acetate, ethylene acrylic acid, ethylene methyl acrylate and ethylene n-butyl acrylate copolymers containing 12 to 50% comonomer.

10 16. The adhesive of Claim 10 wherein there is also present up to 20% by weight of a polymer selected from the group consisting of polyvinyl alcohol, hydroxyethyl cellulose, polyvinyl methyl ether, poly(ethylene oxide), or poly(hydroxy butyrate hydroxy valerate).

15 17. The adhesive of Claim 11 wherein there is also present up to 20% by weight starch or modified starch.

18. A non-pressure sensitive adhesive composition comprising 20-98% by weight of a polylactide homo- or copolymer containing at least 20 molar percent lactide,
20 2-80% tackifying resin, 0-30% of a wax-like diluent, 0-25% plasticizer and 0 to 3% stabilizer.

19. The adhesive of Claim 18 wherein the polylactide is poly(l-lactide) or a copolymer thereof.

20. The adhesive of Claim 18 wherein the tackifying
25 resin is a terpene-phenolic resin or rosin derivative, the plasticizer is a phenyl ether of poly(ethylene glycol) or the methyl ester of hydrogenated wood rosin and the wax diluent is hydrogenated castor oil.

21. The adhesive of Claim 18 wherein there is also
30 present up to 20% by weight of a thermoplastic polymer selected from the group consisting of ethylene vinyl

SUBSTITUTE SHEET

acetate, ethylene acrylic acid, ethylene methyl acrylate and ethylene n-butyl acrylate copolymers containing 12 to 50% comonomer as well as polycaprolactone.

22. The adhesive of Claim 18 wherein there is also
5 present up to 20% by weight of a polymer selected from the group consisting of polyvinyl alcohol, hydroxyethyl cellulose, polyvinyl methyl ether, poly(ethylene oxide), or poly(hydroxy butyrate hydroxy valerate).

23. The adhesive of Claim 18 wherein there is also
10 present up to 20% by weight starch or modified starch.

INTERNATIONAL SEARCH REPORT

Int. l. Application No
PCT/US 93/08913

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 C09J167/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 5 C09J C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO,A,90 01521 (BATELLE MEMORIAL INSTITUTE) 22 February 1990 see claims 1-46 ---	1-9, 11-16, 18-22
Y	GB,A,2 099 436 (DAICEL CHEMICAL INDUSTRIES LTD) 8 December 1982 see page 1, line 40 - line 41; claims 1-7 ---	1-9, 11-16, 18-22
A	US,A,4 156 676 (BACSKAI) 29 May 1979 see claims 1-3 ---	1
P,A	US,A,5 169 889 (KAUFFMAN ET AL) 8 December 1992 see claims 1-11 --- -/--	1-23

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

20 December 1993

Date of mailing of the international search report

30. 12. 93

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl.
Fax (+ 31-70) 340-3016

Authorized officer

Decocker, L

INTERNATIONAL SEARCH REPORT

Int. l. Application No
PCT/US 93/08913

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passage	Relevant to claim No.
P,A	WO,A,92 19680 (NOVAMONT S.P.A.) 12 November 1992 see page 4, line 12 - line 17; claims 1,2 -----	1-23

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Application No

PCT/US 93/08913

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9001521	22-02-90	AU-B- 634723	04-03-93
		EP-A- 0428620	29-05-91
		JP-T- 4504731	20-08-92
		US-A- 5216050	01-06-93
		US-A- 5180765	19-01-93
		US-A- 5252642	12-10-93

GB-A-2099436	08-12-82	JP-A- 57200449	08-12-82
		JP-B- 1007106	07-02-89
		JP-C- 1524559	12-10-89
		JP-A- 57200450	08-12-82
		DE-A- 3220324	30-12-82
		GB-A,B 2140430	28-11-84
		US-A- 4511687	16-04-85

US-A-4156676	29-05-79	BE-A- 874314	18-06-79
		CA-A- 1123133	04-05-82
		DE-A- 2911371	11-10-79
		FR-A,B 2421201	26-10-79
		GB-A,B 2017729	10-10-79
		JP-C- 1128684	24-12-82
		JP-A- 54131657	12-10-79
		JP-B- 57017029	08-04-82
		NL-A- 7901985	01-10-79

US-A-5169889	08-12-92	AU-A- 2134492	29-07-93
		CA-A- 2079535	28-07-93
		EP-A- 0553394	04-08-93

WO-A-9219680	12-11-92	EP-A- 0525245	03-02-93
		AU-A- 1650992	21-12-92
		AU-A- 2058292	04-02-93
		CA-A- 2084994	04-11-92
		EP-A- 0539541	05-05-93
		JP-A- 5228205	07-09-93
		EP-A- 0512360	11-11-92
		JP-A- 5123550	21-05-93
		EP-A- 0560244	15-09-93

Form PCT/ISA/210 (patent family annex) (July 1992)

THIS PAGE BLANK (USPTO)